

Sponsor:
Matthew
ACME Magentic Tapes Ltd
84 Fuk Hi Street
Yuen Long Industrial Estate, Wang Chow
Yuen Long N.T.
Hong Kong

Latex Particle Challenge Final Report

Test Article: Disposable medical mask

Study Number: 1283079-S01 Study Received Date: 31 Mar 2020

Testing Facility: Nelson Laboratories, LLC 6280 S. Redwood Rd.

Salt Lake City, UT 84123 U.S.A.

Test Procedure(s): Standard Test Protocol (STP) Number: STP0005 Rev 07

Deviation(s): Quality Event (QE) Number(s): QE22125

Summary: This procedure was performed to evaluate the non-viable particle filtration efficiency (PFE) of the test article. Monodispersed polystyrene latex spheres (PSL) were nebulized (atomized), dried, and passed through the test article. The particles that passed through the test article were enumerated using a laser particle counter.

A one-minute count was performed, with the test article in the system. A one-minute control count was performed, without a test article in the system, before and after each test article and the counts were averaged. Control counts were performed to determine the average number of particles delivered to the test article. The filtration efficiency was calculated using the number of particles penetrating the test article compared to the average of the control values.

The procedure employed the basic particle filtration method described in ASTM F2299, with some exceptions; notably the procedure incorporated a non-neutralized challenge. In real use, particles carry a charge, thus this challenge represents a more natural state. The non-neutralized aerosol is also specified in the FDA guidance document on surgical face masks. All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side: Inside
Area Tested: 91.5 cm²
Particle Size: 0.1 µm

Laboratory Conditions: 20°C, 24% relative humidity (RH) at 0743; 20°C, 24% RH at 0925

Average Filtration Efficiency: 99.68% Standard Deviation: 0.021

lac-MRA

ANAB A C C R E D I T E D TESTING LABORATORY

Study Director

Curtis Gerow, B.S.

Study Completion Date

1283079-S01

sales@nelsonlabs.com

FRT0005-0001 Rev 6



Deviation Details: Controls and sample counts were conducted for one minute instead of an average of three one minute counts. This change shortens the total test time for each sample but will still provide an accurate determination of the particle counts. An equilibrate is a dwell period where the challenge is being applied to the test article for a certain period of time before test article counts are counted. The equilibrate period was reduced from 2 minutes to a minimum of 30 seconds which is sufficient time to clear the system of any residual particles, and establish a state of stable equilibrium before sample counts are taken. Test method acceptance criteria were met, results are valid.

Results:

Test Article Number	Test Article Counts	Average Control Counts	Filtration Efficiency (%)
1	37	12,774	99.71
2	45	13,083	99.66
3	43	12,992	99.67
4	43	12,760	99.66
5	39	12,259	99.68