

ACME MAGNETIC TAPES LTD.

AUDIO MAGNETIC TAPE SPECIFICATIONS

MS-1080

<u>Measuring Condition</u>	Unit	C60	C90
1.Tape speed	cm/s	4.76	
2.Track Width	mm	0.6	
3.Gap Length:			
Record head	μm	3.0	
Playback head	μm	1.5	
4.Playback Equalization	μs	120+3180	
5.Reference Tape		IEC-IR723DG	
<u>Electroacoustic Properties</u>			
1.working Bias	%	100(+0/-10)	
2.Sensitivity at 315Hz	dB	> -1.3	> -1.0
3.Frequency Response			
at 8KHz	dB	≅ +1.0	≅ +1.0
at 12KHz	dB	≅ +1.6	≅ +1.6
4.Maximum output level at			
315Hz,THD:5%	dB	≅ +3.5	≅ +3.5
5.Saturation level at 8KHz	dB	≅ -4.5	≅ -4.5
10KHz	dB	≅ -6.5	≅ -6.5
6.Signal to noise ratio	dB	< -50	
<u>Magnetic properties</u>			
1.Coercivity (Hc)	Oe	375(±15)	375(±15)
2.Rententivity(Br)	Gs	1300	1300
3.Squareness(Br/Bs)		0.86(±0.2)	0.86(±0.2)
<u>Physical properties</u>			
1.Base material		Semi Tensilized	Semi Tensilized
		Polyester film	Polyester film
2.Tape width	mm	3.81(+0/-0.05)	
3.Base thickness	μm	11.0(±0.7)	7.5(±0.7)
4.Coating thickness	μm	4.3(±0.5)	4.2(±0.5)
5.Total thickness	μm	15.3(±0.7)	11.7(±0.7)
6.Base film specifications:			
Yield strength	kg	0.5	0.3
Breaking strength	kg	1.0	0.7
Residual elongation	%	-	
7.Color	-	Tan	Tan
8.Surface Resistance	Ω/Sq	≅ 4.0×10 ¹⁰	≅ 4.0×10 ¹⁰

NOTE:Specifications may be varied without prior notice.